



MY Polymers Products Selector Guide

MY-130 Series

	MY-132	MY-132A	MY-133	MY-133 V-2000	MY-133 V5000	MY-136	MY-136 V2000	MY-1375	MY-1375 V2000	MY-139
n^D liquid	1.319	1.324	1.3315	1.3293	1.339	1.355	1.359	1.369	1.369	1.379
n^D cured @589nm	1.324	1.326	1.336	1.3330	1.344	1.365	1.369	1.379	1.380	1.391
RI cured @950 nm	1.320	1.322	1.332	1.329	1.340	1.361	1.363	1.375	1.375	1.386
Density, g/cm³	1.73	1.73	1.67	1.71	1.66	1.57	1.58	1.55	1.54	1.50
Viscosity, cp	200	2600	700	2-3,000	4500	700	2350	4200	2000	2300
Shore A	62	30	65	70	70	76	95	95	95	
Shore D						26	50		55	58
Adhesion to glass, 90° peel, g/cm	3	4	3	4	6	38	35	26	25	20
Tensile, MPa		0.3	0.4	1.2	1.8	4.7	6.6	9.5	9.0	11.3
Elongation to break, %	10	80	12	40	54	83	28	52	40	38
Elastic Modulus, MPa	2.5	0.4	4	4.5	3.6	11	92	108	110	190



Electro Optical Components, Inc.

5460 Skylane Boulevard, Santa Rosa, CA 95403
 Phone: (707) 568-1642 • FAX: (707) 568-1652
www.eoc-inc.com



MY Polymers Products Selector Guide

MY-140 Series

	MY-142	MY-142B	MY-143	MY-145	MY-146	MY-1465	MY-147	MY-1473	MY-148	MY-149
n^D liquid	1.410	1.405	1.423	1.434	1.4427	1.4462	1.4527	1.4558	1.461	1.476
n^D cured @589nm	1.420	1.420	1.435	1.450	1.4607	1.465	1.4700	1.4738	1.479	1.492
D, g/cm³	1.24	1.37	1.18	1.15	1.125	1.08	1.094	1.09	1.075	1.03
Viscosity, cps	1050	600	1200	630	270	235	500	290	320	1000
Shore A	70		80	92	91	90				80
Shore D		71		50	62	45	60	60	65	
Adhesion to glass, 90° peel, g/cm	95	42	300	600	>1400	>800	>1000	1700	1000	600
Tensile Strength, MPa	3.7	21		11.4	17.4	10.6	11.6	14.8	16.7	
Elongation to break,%	100	9.5		150	22	140	174	90	90	
Elastic modulus, MPa	5.3	525		300	515	160	270	555	580	



Electro Optical Components, Inc.

5460 Skylane Boulevard, Santa Rosa, CA 95403
 Phone: (707) 568-1642 • FAX: (707) 568-1652
www.eoc-inc.com



MY Polymers Products Selector Guide

OF Series for Optical Fiber Cladding

	OF-133	OF-134	OF-136	OF-1375	OF-139
n^D liquid (@589 nm)	1.333	1.339	1.359	1.368	1.386
n^D cured (@589 nm)	1.334	1.344	1.369	1.377	1.397
RI curd at 950 nm	1.330	1.340	1.363	1.372	1.392
Density, g/cm³	1.68	1.66	1.58	1.56	1.47
Viscosity, cp	2100	3800	2600	3300	5000
Hardness, Shore	70-75A	70-75A	90-95A	90-95A	60D
Adhesion to glass, 90° Peel, g/cm	20	33	64	120	90
Tensile Strength, MPa	0.9	1.1	6.9	8.3	15
Elongation to break, %	20	38	39	54	55
Elastic modulus, MPa	3.7	3.8	100	105	292
Hard Coating Requirement	Yes	Yes	No	No	No



Electro Optical Components, Inc.

5460 Skylane Boulevard, Santa Rosa, CA 95403
 Phone: (707) 568-1642 • FAX: (707) 568-1652
www.eoc-inc.com